

AMENDMENTS TO THE SPECIFICATION

Please amend Table 1 of the specification at page 23, as it appears on the following page:

Table 1

CHEMICAL CONSTITUENTS (MASS %) OF STAINLESS STEEL WIRE

Type of steel	C	Si	Mn	Ni	Cr	Mo	Nb	Ti	Co	Al	N	C+N
a	0.07	0.37	1.25	8.34	18.17	0.16	-	-	-	-	0.17	0.24
b	0.07	0.37	1.21	10.34	17.80	1.5	-	-	-	-	0.20	0.27
c	0.07	0.37	1.24	8.45	18.17	-	1.0	-	-	-	0.21	0.28
d	0.08	0.37	1.31	8.52	18.17	-	-	0.5	-	-	0.20	0.28
e	0.07	0.95	1.11	8.04	18.17	-	-	-	-	-	0.19	0.27
f	0.07	0.89	1.26	8.34	18.17	1.5	-	-	-	-	0.21	0.28
g	0.07	0.90	1.25	8.34	18.17	0.5	-	-	0.5	-	0.19	0.26
h	0.07	0.28	1.21	8.64	18.32	0.22	-	-	-	-	0.02	0.09
i	0.10	0.25	1.31	8.30	18.56	0.20	-	-	-	-	0.27	0.37
j	0.04	0.61	1.39	11.76	17.72	2.10	-	-	-	-	0.02	[[0.6]] 0.06
k	0.08	0.17	0.80	8.08	16.48	-	-	-	-	1.2	0.01	0.10